Anti Graffiti

Anti Graffiti is a Solvent Based System for Polished and Unpolished Surface.

Technical Specification

Formulated with Silicone dispersed in Hydrocarbon.

Advantages

- Advanced Anti-Graffiti Surface Protection Technology
- Prevents Permanent Graffiti & Marker Stains
- Weak Bonding Technology for Easy Cleaning of Gums & Adhesives
- Protects Surfaces from Paint, Ink & Dirt Penetration
- Creates a Durable Protective Surface Barrier
- Breathable Protection with Long-Lasting Performance
- UV & Weather Resistant for Exterior Durability
- Ideal for High-Traffic & Public Areas
- Easy-to-Clean & Low Maintenance Performance
- Excellent for Vertical application.
- Low VOC Formula with Advanced Surface Safety
- Easy-to-use.

Where to Use

- ✓ Sand Stone
- ✓ Concrete

Technical Data

- Appearance: Clear, liquid
- Odor less
- Specific gravity at 20°C: ca. 0.80 g/cm³
- Application Temperature 15-30 °C
- Drying time 4 Hr.
- Curing Time 24 Hr.

Directions for Use

- Read the entire label and follow directions.
- Carry out a patch test on a small area first.
- Allow grout to cure for 72 hours before use.
- Ensure the surface is clean and dry.
- Apply within 20°C–30°C temperature range.
- Maintain proper ventilation during application.

How To Use

- **Apply Sealer:** Spread one coat evenly till the surface is drenched for full coverage.
- **Penetration Time**: Allow 25–30 minutes to soak in.
- **Curing:** Let it cure for 72 hours before use.

Typical Coverage

- Sand Stone 5- 10* Sq Mt Per Ltr.
- Concrete 5- 10* Sq Mt Per Ltr

Note: Above mentioned coverage may differ depending on porosity, type of polish and application method.

Trinity Rubber
Plot No. J - 2314, Phase - III, G.I.D.C. Area, Vapi 396195

70963 34083

info@waterrepellent.in

Application Method

Brush: Paint Brush with Soft Bristle.
Spray Machine: Low Pressure High Volume
Fabric Roller: Short Bristle.

Pack Size

- 1 LTR
- 5 LTR
- 20 LTR
- 30 LTR
- 50 LTR

Standard Testing Method

- **Water Repellency:** ASTM C67 or ASTM C140
- **Stain Resistance:** ASTM D1308
- **Breathability:** ASTM E96
- **UV Resistance:** ASTM G154
- **Accelerated Weathering:** ASTM G155

Caution

- Keep out of reach of children.
- Do not disperse into the environment after use.
- Flammable.

Trinity Rubber
Plot No. J - 2314, Phase - III, G.I.D.C. Area, Vapi 396195

70963 34083

info@waterrepellent.in